

# 4800 BOLTARON 4800

## GENERAL INFORMATION

Boltaron 4800 is a proprietary, fire retardant, extruded Acrylic/PVC alloy sheet designed specifically for mass transit and aircraft interior applications. Boltaron 4800 meets ASTM E-162 and ASTM E-662 stringent requirements for flammability and low smoke emissions and FTA, UMTA and Docket 90A guidelines. Boltaron 4800 offers excellent impact strength, abrasion resistance, stain and chemical resistance, and thermoformability.

## AVAILABILITY

Colors: Custom  
Gauges: .040 to .250  
Widths: Up to 60"  
Lengths: Up to 120"  
Custom Sizes: Upon request  
Textures: Coarse Matte (CM)  
Felt (FT)  
Haircell (HC)  
Levant (LT)  
Mesa (MS)  
Suede (SD)

## SUGGESTED APPLICATIONS

Seatbacks  
Dashboards  
Partitions  
Ceiling Panels  
Tray Tables  
Window Reveals  
Storage Compartments

## Typical Physical Properties

Property	Test Method	Typical values
Specific gravity	ASTM D-792	1.435
Tensile strength (PSI)	ASTM D-638	4,900-5,200
Flexural strength (PSI)	ASTM D-790	7,800-8,400
Flexural modulus (PSI)	ASTM D-790	3.0-3.3x10 <sup>5</sup>
Izod impact (Ft. lbs./in. of notch)	ASTM D-256	3-5
Gardner Drop	ASTM D-2039	>320
Hardness Rockwell R	ASTM D-785	102-104
Heat Deflection (°F) 264 PSI (annealed)	ASTM D-648	165-168
Radiant Panel Flame Spread Index	E-162	<10
NBS Smoke (1/8")	E-662 Smoldering Mode	<100 DS @ 90 sec. <200 DS @ 4 min.
	Flame Mode	<100 DS @ 90 sec. <200 DS @ 4 min.
LNE "M"	P92 - 507	M1
MVSS 302		PASS
Flammability UL	UL-94	V-0 <sup>1</sup>
Forming Temperature (°F) □		335-365

<sup>1</sup>Independent Lab Testing

One General Street, Newcomerstown, OH 43832  
P 800.342.7444 F 740.498.5448 E info@boltaron.com  
[www.boltaron.com](http://www.boltaron.com)

## LIMITATION OF WARRANTY

The application suggestions, specifications and other data described here are based upon experience and information that is believed, by BPP to be reliable. However, BPP makes no express or implied warranty that BOLTARON 4800 will perform in accordance with such specifications in any particular circumstance. Therefore, ALL EXPRESS OR IMPLIED WARRANTIES IN CONNECTION WITH BOLTARON 4800, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY DISCLAIMED. The prospective user should determine the suitability of BOLTARON 4800 and the application suggestions before actual application.