

NP310HT

TECHNICAL DATA BULLETIN

GRADE: NP310HT

NEMA: C

U.L. LISTED: N

DESCRIPTION: Canvas machining grade for structural and mechanical applications. NP310HT has better impact strength than phenolic paper grades. It meets the requirements of MIL-I-24768/16, IEC-60893-4-PF CC 201 and is designed to meet GE specification A19B15B1.

TYPICAL PROPERTIES

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
PHYSICAL PROPERTIES					
Specific Gravity (ASTM D792)		-			1.37
Rockwell Hardness (ASTM D785)	0.250" Build-up	M Scale	100		
Moisture Absorption (ASTM D570)	Condition A	%	3.40	1.80	0.80
Flexural Strength (ASTM D790)	Condition A LW / CW	psi (MPa)	18,000 / 18,000 (124.1) / (124.1)		
Flexural Modulus (ASTM D790)	Condition A LW / CW	kpsi (GPa)	2,500 / 2,400 (17.2) / (16.5)		
Izod Impact Strength (ASTM D256)	Condition A LW / CW	ft-lb/in (J/cm)			
	Condition E-48/50 LW / CW	ft-lb/in (J/cm)			2.35 / 2.02 (1.25) / (1.08)
Compressive Strength (ASTM D695)	Condition A Flatwise	psi (MPa)			35,000 (241.3)
Bonding Strength (ASTM D229)	Condition A	lb (kg)			2,700 (1,224.7)
	Condition D-48/50	lb (kg)			2,400 (1,088.6)

TECHNICAL DATA BULLETIN

GRADE: NP310HT

NEMA: C

U.L. LISTED: N

TYPICAL PROPERTIES (continued)

	UNITS	VALUE		
		Thickness Tested		
		0.0625"	0.125"	0.500"
THERMAL PROPERTIES				
Temperature Index ¹ (UL Bulletin 746b) Electrical / Mechanical	°C	125 / 125		
Flammability Rating Condition A (UL Bulletin 94)	Class	HB		
ELECTRICAL PROPERTIES				
Breakdown Voltage Condition A (ASTM D149)	kVolts	55		
Electric Strength Condition A (ASTM D149)	Volts/mil (kV/cm)	527 (207.5)		

¹ This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, www.norplex-micarta.com, to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.