



Technical Data Sheet

Halar® 902

ethylene chlorotrifluoroethylene copolymer



SOLVAY

asking more from chemistry®

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.71		ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (275°C/5.0 kg)	8.0 to 13	g/10 min	ASTM D1238
Molding Shrinkage - Flow	2.5	%	ASTM D955
Water Absorption (Equilibrium)	< 0.10	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus ² (23°C)	1660	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield, 23°C	30.0	MPa	
Break, 23°C	47.0	MPa	
Tensile Elongation ²			ASTM D638
Yield, 23°C	5.0	%	
Break, 23°C	250	%	
Flexural Modulus ³ (23°C)	1690	MPa	ASTM D790
Flexural Strength ³ (23°C)	47.0	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.20		
vs. Itself - Static	0.20		
Taber Abrasion Resistance			
1000 Cycles, 500 g, CS-17 Wheel	5.00	mg	

Impact	Typical Value	Unit	Test method
Notched Izod Impact			ASTM D256
-40°C, 3.20 mm	210	J/m	
23°C, 3.20 mm	No Break		

Hardness	Typical Value	Unit	Test method
Rockwell Hardness (R-Scale)	90		ASTM D785
Durometer Hardness (Shore D)	75		ASTM D2240

Halar® 902

ethylene chlorotrifluoroethylene copolymer

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	90.0	°C	
1.8 MPa, Unannealed	65.0	°C	
Brittleness Temperature	< -76.0	°C	ASTM D746A
Glass Transition Temperature	85.0	°C	DMA
Melting Temperature	225	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	205	°C	ASTM D3418
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696
Specific Heat (23°C)	962	J/kg/°C	ASTM D3418
Thermal Conductivity (40°C)	0.15	W/m/K	ASTM C177
Crystallization Heat	28.0	J/g	ASTM D3418
Heat of Fusion	28.0	J/g	ASTM D3418
Thermal Stability - 1% mass loss, N2	405	°C	TGA

Electrical	Typical Value	Unit	Test method
Volume Resistivity ⁴ (23°C)	5.5E+16	ohms-cm	ASTM D257
Dielectric Strength (23°C, 3.20 mm)	14	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 MHz)	2.57		ASTM D150

Electrical	Typical Value	Unit	Test method
Volume Resistivity ⁴ (23°C)	5.5E+16	ohms-cm	ASTM D257
Dielectric Strength (23°C, 3.20 mm)	14	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 MHz)	2.57		ASTM D150

Flammability	Typical Value	Unit	Test method
Flame Rating	V-0		UL 94
Oxygen Index	52	%	ASTM D2863

Notes

Typical properties: these are not to be construed as specifications.

¹ Under 5 Kg

² 50 mm/min

³ 2.5 mm/min

⁴ 50% RH

Order Online from Professional Plastics, Inc.
<https://www.professionalplastics.com/HALAR-ECTFE>



www.professionalplastics.com

sales@proplas.com

USA (888) 995-7767 – Singapore +65 6266-6193 – 台灣 Taiwan +886 (3) 5357850