

## **HONEYCOMB PANELS - HIGH TEMPERATURE GRADE**

**High Temperature Honeycomb Panels** are manufactured to resist tooling temperatures up to 425°F/218°C. This Honeycomb panel is fabricated with fiberglass skins and high-temperature resins. A perforated, corrosion-resistant core and 2 plies of 10-ounce fiberglass cloth provide strength and stability. This material is bonded under pressure for greater peel strength. Peel ply is applied for good bonding surface, and the panel is staged post cured to 425°F/218°C. Honeycomb Panels are manufactured by Reklein Plastics.



#### SPECIFICATIONS:

High Temperature Honeycomb Panels meet Boeing MMS 101 specifications.

#### STANDARD SIZES AVAILABLE:

1/2", 3/4", 1", 2" T x 48" W x 96" L

### STORAGE:

Store all honeycomb panels on a flat surface at 60°F - 100°F.

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to make their own test to determine

the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the products failure to conform to any particular specifications.

# Order Online at:

www.professionalplastics.com/HighTemperatureHoneycombPanels

www.professionalplastics.com

sales@proplas.com

USA (888) 995-7767 - Singapore +65 6266-6193 - 台湾 Taiwan +886 (3) 5357850