

>> LIGHTWEIGHT, COST-EFFECTIVE AND EASILY FABRICATED

BOROTRON® BORATED PE

Key Benefits

Key Benefits

- Easy to handle and fabricate
- Durable over a wider temperature range
- Consistent density and homogeneity
- Superior dimensional quality and flatness
- Available as 48" x 96" sheets for simple installation in most applications

Common Applications

- Medical vaults and doors
- Hot cells
- Nuclear storage and transport containers
- Nuclear detection systems
- Particle accelerators

Note:

Materials with a high hydrogen density are also used as a component in neutron shielding systems. If you are looking for the broadest range of sizes and shapes in unfilled hydrogen rich material, Quadrant can meet your needs with TIVAR® 1000.

Borotron® Borated PE

Borotron® Borated PE has been used as a medical and industrial shielding material to attenuate and absorb neutron radiation. This easily fabricated polymer material also offers designers greater durability and function over a wider range of temperatures than traditional materials.

Borotron® HD050 is based on Quadrant's high performance HDPE with 5% elemental boron. ●

Learn more at www.quadrantplastics.com



QUADRANT

Borotron® is a registered trademark of the Quadrant group of companies
© 2008, the Quadrant group of companies

Quadrant Engineering Plastic Products

Data Sheet - Borotron® HD050 Borated PE

**Typical
Average
Value**

	Property	Units	Test Method	
Mechanical Properties	Specific Gravity, 73°F	-	ASTM D792	1.01
	Tensile Strength, 73°F	psi	ASTM D638	2,400
	Tensile Modulus of Elasticity, 73°F	psi	ASTM D638	111,200
	Tensile Elongation (at break), 73°F	%	ASTM D638	3.9
	Flexural Strength, 73°F	psi	ASTM D790	4,200
	Flexural Modulus of Elasticity, 73°F	psi	ASTM D790	126,500
	Compressive Strength, 10% Deformation, 73°F	psi	ASTM D695	3,500
	Compressive Modulus of Elasticity, 73°F	psi	ASTM D695	97,400
	Hardness, Durometer, Shore "D" Scale, 73°F	-	ASTM D2240	71
Izod Impact (notched), 73°F	ft.lb./in.	ASTM D256 Type "A"	0.9	
Thermal Properties	Coefficient of Linear Thermal Expansion (-40°F to 300°F)	in./in./°F	ASTM E-831 (TMA)	1.1 x 10 ⁻⁵
	Heat Deflection Temperature 264 psi	°F	ASTM D648	
	Melting Point (crystalline) peak	°F	ASTM D3418	260
	Continuous Service Temperature in Air (Max.) (1)	°F	-	180
Electrical Properties	Service Resistivity	ohms/square	ASTM D257	>10 ¹²
	Flammability @ 3.1 mm (1.8 in.) (3)	-	UL94	HB
Miscellaneous	Water Absorption Immersion, 24 Hours	% by wt.	ASTM D570 (2)	<0.01
	Water Absorption Immersion, Saturation	% by wt.	ASTM D570 (2)	<0.01

(1) Data represents Quadrant's estimated maximum long-term service temperature based on practical field experience.

(2) Specimens: 1/8" thick x 2" diameter or square.

(3) Estimated rating based on available data. The UL94 Test is a laboratory test and does not relate to actual fire hazard. Contact Quadrant for specific UL "Yellow Card" recognition number.

IMPORTANT: All information supplied by or on behalf of Quadrant Engineering Plastic Products in relation to its products, in any form, is supported by research and believed to be reliable, but Quadrant Engineering Plastic Products assumes no liability whatsoever in respect of application, processing, or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing, or use of the aforementioned information or product and the seller makes no warranties, express or implied, including, but not limited to, the implied warranties of merchantability and fitness for a particular purpose. The end user must confirm with a certified professional that this material meets the necessary criteria for their proposed neutron shielding application. Full-scale testing and end product performance are the responsibility of the end user. No liability whatsoever shall attach to Quadrant Engineering Plastic Products for any infringement of the rights owned or controlled by a third party in intellectual, industrial, or other property by reason of the application, processing, or use of the aforementioned information or products by the buyer. Customers should review the corresponding Material Safety Datasheet to ensure they are aware of the flammability properties of the material and to ensure they handle and work with the material in a safe manner.

As a result of our internal continuous improvement programs, availability and gathering of new and/or additional technical data, knowledge, and experience, as well as changing market requirements and revised internationally recognized material/test standards, Quadrant Engineering Plastic Products is extending and updating its literature and technical information on a continuous basis. We therefore invite and recommend our customers to consult our website for the latest and up to date information on our materials.

Distributed by:



QUADRANT

Borotron® is a registered trademark of the Quadrant group of companies
© 2008, the Quadrant group of companies

Quadrant Engineering Plastic Products