

### Optical Clear Sheet

MAKROLON<sup>®</sup> OP Sheet is a clear polished surface, transparent, UV stabilized, polycarbonate product. It features outstanding impact strength, and superior dimensional stability. MAKROLON OP Sheet has a five (5) year warranty against breakage. The terms of the warranty against breakage are set forth in the warranty, which is available upon request.


### Applications

Industrial and structural applications, including thermoformed and fabricated components

Typical Properties			
Property	Test Method	Units	Values
<b>PHYSICAL</b>			
Specific Gravity	ASTM D792	-	1.2
Refractive Index	ASTM D542	-	1.586
Light Transmission, Clear @ 0.125"	ASTM D1003	%	86
Light Transmission, Gray, Bronze	ASTM D1003	%	50
Light Transmission, Dark Gray	ASTM D1003	%	18
Water Absorption, 24 hrs	ASTM D570	%	0.15
Poisson's Ratio	ASTM E132	-	0.38
<b>MECHANICAL</b>			
Tensile Strength, Ultimate	ASTM D638	psi	9,500
Tensile Strength, Yield	ASTM D638	psi	9,000
Tensile Modulus	ASTM D638	psi	340,000
Elongation	ASTM D638	%	110
Flexural Strength	ASTM D790	psi	13,500
Flexural Modulus	ASTM D790	psi	345,000
Compressive Strength	ASTM D695	psi	12,500
Compressive Modulus	ASTM D695	psi	345,000
Izod Impact Strength, Notched @ 0.125"	ASTM D256	ft-lbs/in	18
Izod Impact Strength, Unnotched @ 0.125"	ASTM D256	ft-lbs/in	60 (no failure)
Instrumented Impact, 0.125"	ASTM D3763	ft-lbs	>46
Shear Strength @ Yield	ASTM D732	psi	6,000
Shear Strength, Ultimate	ASTM D732	psi	10,000
Shear Modulus	ASTM D732	psi	114,000
Rockwell Hardness	ASTM D785	-	M70/R118
<b>THERMAL</b>			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75 x 10 <sup>-5</sup>
Coefficient of Thermal Conductivity	ASTM C177	BTU·in/hr·ft <sup>2</sup> ·°F	1.35
Heat Deflection Temperature @ 264 psi	ASTM D648	°F	270
Heat Deflection Temperature @ 66 psi	ASTM D648	°F	280
Brittleness Temperature	ASTM D746	°F	-200
Shading Coefficient, Clear 0.125"	ASHRAE	-	1.02
Shading Coefficient, Gray, Bronze 0.125"	ASHRAE	-	0.70
U factor 0.25" (summer gain, winter loss)	ASTM D1363	BTU/hr·ft <sup>2</sup> ·°F	0.90, 0.96

# Product Data

## MAKROLON<sup>®</sup> OP Sheet



### Disclaimer

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.



MAKOP 0710

**Sheffield Plastics**  
A Bayer MaterialScience LLC Business

119 Salisbury Road  
Sheffield, MA 01257  
800-254-1707  
Fax: 800-457-3553  
Web site: [www.sheffieldplastics.com](http://www.sheffieldplastics.com)  
E-mail: [info@sheffieldplastics.com](mailto:info@sheffieldplastics.com)

©Copyright, 2010  
Bayer, The Bayer Cross and MAKROLON<sup>®</sup> are registered trademarks of Bayer Corporation