



# Makrolon® AU sheet

## Abrasion resistant ultra clear

Makrolon® AU sheet is a one side, hard coated polycarbonate product exhibiting unsurpassed visible light transmission versus other polycarbonate sheet products. This high clarity sheet is specifically designed for use in multilayer laminates. The advanced hard coat technology significantly enhances the abrasion resistance, chemical resistance, and weathering properties of the product while maintaining the excellent impact performance of Makrolon polycarbonate.

## Applications


Specialty laminates

Typical Properties*			
Property	Test Method	Units	Values
<b>PHYSICAL</b>			
Specific Gravity	ASTM D 792	–	1.2
Refractive Index @ 72°F	ASTM D 542	–	1.586
Light Transmission, Clear @ 0.125"	ASTM D 1003	%	91
Water Absorption, 24 hours @ 73°F	ASTM D 570	%	0.15
Taber Abrasion @ 100 Cycles, Delta Haze CS-10F Wheel @ 500 gm load	ASTM D 1044	%	2
<b>MECHANICAL</b>			
Tensile Strength, Break	ASTM D 638	psi	9,500
Tensile Strength, Yield	ASTM D 638	psi	9,000
Tensile Modulus	ASTM D 638	psi	340,000
Elongation	ASTM D 638	%	110
Flexural Strength	ASTM D 790	psi	13,500
Flexural Modulus	ASTM D 790	psi	345,000
Compressive Strength	ASTM D 695	psi	12,500
Compressive Modulus	ASTM D 695	psi	345,000
Izod Impact Strength, Notched @ 0.125"	ASTM D 256	ft-lbs/in	18
<b>THERMAL</b>			
Coefficient of Thermal Expansion	ASTM D 696	in/in/°F	3.75 x 10 <sup>-5</sup>
Heat Deflection Temperature @ 264 psi	ASTM D 648	°F	270
Heat Deflection Temperature @ 66 psi	ASTM D 648	°F	280

\*Typical Properties are not intended for specification purposes


# Makrolon® AU sheet

## Impact Resistance\*




\*Instrumented Impact per ASTM D 3763, sample thickness 0.125" nominal

## Abrasion Resistance\*



\*Taber Abrasion per ASTM D 1044, 100 cycles, CS-10F wheel

## Weathering Behavior of Makrolon® in Vertical Orientation



\*Based upon Xenon WOM accelerated weathering for UV dose at mid-latitude location

## Chemical Resistance\*


Chemical Tested	Resistance Time
-----------------	-----------------

Acetone	>24 hrs
Ammonia (10% concentration)	>24 hrs
Antifreeze (50/50)	>24 hrs
Benzene	>24 hrs
Bleach (Clorox concentrated)	>24 hrs
Chloroform	>24 hrs
Denatured Alcohol	>24 hrs
Di (2-ethylhexyl) phthalate	>24 hrs
Diesel Oil	>24 hrs
Isopropyl Alcohol (IPA)	>24 hrs
Kerosene	>24 hrs
Methyl Alcohol	>24 hrs
Methyl Butyl Ketone	>24 hrs
Methyl Ethyl Ketone	>24 hrs
Methylene Chloride	>24 hrs
Naphthalene, 1-bromo-	>24 hrs
Potassium Hydroxide - Lye (10%)	>24 hrs
Sodium Hydroxide (10%)	>24 hrs
Toluene	>24 hrs
Turpentine	>24 hrs
Unleaded Gasoline (87 Octane)	>24 hrs
Vinegar	>24 hrs
Xylene	>24 hrs
<b>Acids:</b>	
Hydrochloric Acid (20%)	>24 hrs
Nitric Acid (20%)	>24 hrs
Sulfuric Acid (20%)	>24 hrs

\*Tested in accordance to ASTM D 1308-02

Always keep hazardous chemicals away from uncoated edge of Makrolon Polycarbonate

## Spectral Transmission



119 Salisbury Road  
 Sheffield, MA 01257  
 Toll Free: 800.254.1707  
 Fax: 800.457.3553  
[sfdinfo@covestro.com](mailto:sfdinfo@covestro.com)  
[sheets.covestro.com](http://sheets.covestro.com)

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

With respect to health, safety and environment precautions, the relevant Safety Data Sheets (SDS) and product labels must be observed prior to working with our products.