

## DuPont Fluoroproducts

# DuPont™ Teflon® PFA 450 HP

## fluoropolymer resin



## Extrusion and Molding Resin

### Brand

*Teflon*® is a registered trademark of DuPont for its brand of fluoropolymer resins, which can only be licensed by DuPont for use in approved applications. Customers who wish to use the *Teflon*® trademark in connection with DuPont PFA products under license from DuPont should contact (800) 262-2745. Without a license, customers may not identify their product as containing *Teflon*®, but may refer to the resin as PFA 450 HP.

### Description

DuPont™ *Teflon*® PFA 450 HP fluoropolymer is a special purpose resin available in clear, 2.5-mm (0.1-in.) pellets. This resin is a chemically modified form of *Teflon*® PFA 350 that combines many of the benefits of the parent resin with several new ones. The additional benefits may include enhanced purity, improved thermal stability while processing and chemical inertness, for example, to ozonated fluids. Similar to *Teflon*® PFA 350, this resin has a relatively low flow rate, long flex life, and enhanced resistance to environmental stress cracking compared with most other grades of *Teflon*® PFA.

The enhanced purity of *Teflon*® PFA 450 HP makes it suitable for applications that require improved color, lower extractable fluorides, and freedom from other foreign materials. This product contains no additives and is designed for hostile chemical environments where purity in the parts-per-billion range is needed. Examples are in semiconductor manufacture, fluid handling systems for industry or life sciences, and instrumentation for precise measurements of fluid systems. *Teflon*® PFA 450 HP is preferred when extended service is required in hostile environments involving chemical, thermal, and mechanical stress. **Table 1** shows the typical property data for *Teflon*® PFA 450 HP.

The improved thermal stability of *Teflon*® PFA 450 HP results in reduced amounts of bubbles in final parts and decreased corrosion of processing equipment. *Teflon*® PFA 450 HP combines the processing ease of conventional thermoplastics with properties similar to those of polytetrafluoroethylene.

Properly processed products made from neat *Teflon*® PFA 450 HP resin provide the superior properties typical of fluoropolymer resins: retention of properties after service at 260°C (500°F), useful properties at -196°C (-320°F), and chemical inertness to nearly all industrial chemicals and solvents. Dielectric properties are excellent. Molded products have moderate stiffness and high ultimate elongation.

In a flame situation, products of *Teflon*® PFA 450 HP resist ignition and do not themselves promote flame spread. When ignited by flame from other sources, their contribution of heat is very small and added at a slow rate with very little smoke.

Statements, or data, regarding behavior in a flame situation are not intended to reflect hazards presented by this or any other material when under actual fire conditions.

### Typical End Products

Applications for *Teflon*® PFA 450 HP include tubing; unsupported pipe or pipe linings for production of ultrapure chemicals; semiconductor component handling systems and fluid handling components.



*The miracles of science*®

## Processing

*Teflon*<sup>®</sup> PFA 450 HP can be processed by conventional melt extrusion and by injection, compression, and transfer and blow-molding processes. High melt strength and heat stability permit the use of relatively large die openings and high-temperature draw-down techniques that increase production rates. Reciprocating screw injection molding machines are preferred. Corrosion-resistant metals should be used in contact with molten resin. Extruder barrel should be long, relative to diameter, to provide residence time for heating the resin to approximately 395°C (730°F).

## Safety Precautions

### WARNING!

**VAPORS CAN BE LIBERATED THAT MAY BE HAZARDOUS IF INHALED.**

Before using *Teflon*<sup>®</sup> PFA 450 HP, read the Material Safety Data Sheet and the detailed information in the "Guide to the Safe Handling of Fluoropolymer Resins," latest edition, published by the Fluoropolymers Division of The Society of the Plastics Industry—available from DuPont.

Open and use containers only in well-ventilated areas using local exhaust ventilation (LEV). Vapors and fumes liberated during hot processing, or from smoking tobacco or cigarettes contaminated with *Teflon*<sup>®</sup> PFA 450 HP, may cause flu-like symptoms (chills, fever, sore throat) that may not occur until several hours after exposure and typically pass within about 24 hours. Vapors and fumes liberated during hot processing should be exhausted completely from the work area; contamination of tobacco with polymers should be avoided.

Mixtures with some finely divided metals, such as magnesium or aluminum, can be flammable or explosive under some conditions.

## Storage and Handling

Special product isolation and packaging procedures are used by DuPont to eliminate external contamination of *Teflon*<sup>®</sup> PFA 450 HP resin. Processors also must avoid contamination for successful production of high-purity products.

The properties of *Teflon*<sup>®</sup> PFA 450 HP resins are not affected by storage time. Ambient storage conditions should be designed to avoid airborne contamination and water condensation on the resin when it is removed from containers.

## Freight Classification

*Teflon*<sup>®</sup> PFA 450 HP, when shipped by rail or express, is classified "Plastics, Synthetic, O.T.L., NOIBN." Resin shipped by truck is classified "Plastics, Materials O.T.F.C.E. or S. Granules."

## Packaging

*Teflon*<sup>®</sup> PFA 450 HP resin is packaged in 45.4-kg (100-lb) quantities in drums, each containing two 22.7-kg (50-lb) polyethylene bags. Bulk containers of 726 kg (1,600 lb) will be considered on special request. Special packages containing 2.3 kg (5 lb) and 11.3 kg (25 lb) are also available.

**Table 1**  
**Typical Property Data for DuPont™ Teflon® PFA Fluoropolymer Resin Grade 450 HP**

Property	ASTM Test Method	Unit	Nominal Value
Thermal			
Nominal Melting Point	D3418	°C (°F)	302–310 (575–590)
Coefficient of Linear Thermal Expansion, 21–100°C (70–212°F)	D696	mm/mm/°C (in./in./°F)	14 x 10 <sup>-5</sup> (7.8 x 10 <sup>-5</sup> )
100–149°C (212–300°F)		mm/mm/°C (in./in./°F)	18 x 10 <sup>-5</sup> (9.8 x 10 <sup>-5</sup> )
149–208°C (300–408°F)		mm/mm/°C (in./in./°F)	22 x 10 <sup>-5</sup> (12.1 x 10 <sup>-5</sup> )
Upper Service Temperature	—	°C (°F)	260 (500)
Flow Rate	D3307	g/10 min	2.0
Mechanical			
Tensile Strength, 23°C (73°F)	D3307	MPa (psi)	28 (4,000)
250°C (482°F)		MPa (psi)	14 (2,000)
Specific Gravity	D792	—	2.12–2.17
Tensile Yield Strength, 23°C (73°F)	D3307	MPa (psi)	15.2 (2,200)
Ultimate Elongation, 23°C (73°F)	D3307	%	300
250°C (482°F)		%	500
Flexural Modulus, 23°C (73°F)	D790	MPa (psi)	625 (90,000)
250°C (482°F)		MPa (psi)	69 (10,000)
Hardness Durometer	D2240	—	D55
MIT Folding Endurance			
0.18–0.20 mm (0.007–0.008 in.)	D2176	cycles	500,000*
0.50 mm (0.020 in.)			135,000*
Electrical			
Dielectric Strength			
Short Time, 0.25 mm (0.010 in.)	D149	kV/mm (V/mil)	80 (2,000)
Dielectric Constant, 60–10 <sup>6</sup> Hz	D150	—	2.03
Dissipation Factor, 60–10 <sup>6</sup> Hz	D150	—	0.0001
Volume Resistivity D257	D257	ohm.cm	10 <sup>18</sup>
General			
Water Absorption, 24 hr	D570	%	<0.03
Weather and Chemical Resistance	—	—	Outstanding
Limiting Oxygen Index D2863	%	>95	

\*Depending on equipment and conditions used.

**Note:** Teflon® PFA 450 HP is ASTM D3307, Type II.

Typical properties are not suitable for specification purposes.

Statements, or data, regarding behavior in a flame situation are not intended to reflect hazards presented by this or any other material when under actual fire conditions.

---

**For more information on Fluoroproducts: (302) 479-7731**

DuPont Fluoroproducts  
P.O. Box 80713  
Wilmington, DE 19880-0713  
[www.teflon.com](http://www.teflon.com)

---

***Europe***

DuPont de Nemours Int'l SA  
DuPont Fluoroproducts  
2, chemin du Pavillon  
P.O. Box 50  
CH-1218 Le Grand-Saconnex  
Geneva, Switzerland  
(022) 7175111

***Japan***

DuPont Mitsui  
Fluorochemicals Co., Ltd.  
Chiyoda Honsha Building  
5-18, Sarugaku-cho 1-chome  
Chiyoda-ku, Tokyo 101 Japan  
81-3-5281-5872

***Asia Pacific***

DuPont China, Limited  
26/F., Tower 6, The Gateway  
9 Canton Road, Tsimshatsui  
Kowloon, Hong Kong  
(852) 27341948  
Tim-S.T.Leung@hkg.dupont.com

---

***Canada***

DuPont Canada, Inc.  
DuPont Fluoroproducts  
P.O. Box 2200, Streetsville  
7070 Mississauga Road  
Mississauga, Ontario, Canada  
L5M 2H3  
(905) 821-5194

***South America***

DuPont do Brasil S/A  
Fluoropolymers  
Alameda Itapecuru, 506  
06454-080 - Alphaville  
P.O. Box 263  
Barueri, Sao Paulo, Brazil  
0800-171715  
Produtos.Brazil@bra.dupont.com

---

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

**CAUTION:** Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102.

