

ProLens™

Optical Grade Flame Retardant Polycarbonate Sheet with Abrasion Resistant Hard Coating- 2-Sides.
 Stock in 0.060", 0.080", 0.118" & 0.236"

Applications

Aircraft Window Dust Covers,
 Lenses, Class Dividers

Material Class

A-A-59502 Classification
 Type II Class 1

Colors

Clear, Bronze 5184, Grey 7122

PROPERTIES

TEST METHOD

VALUE

UNITS

Physical Properties

Specific Gravity	ASTM D 792	1.2	-
Water Absorption 73.4 F, 24 hr	ASTM D 570	0.1	%

Mechanical Properties

Tensile Strength	ASTM D 638	9717	psi
Elongation	ASTM D 638	73	%
Flexural Strength	ASTM D 790	14000	psi
Tensile Modules	ASTM D 790	327785	psi
Izod Impact (@.125")	ASTM D 256	18.9	ft-lbs/in
Rockwell Hardness	ASTM D 785	122	R-Scale

Optical Properties

Transmittance	ASTM D 1003	88	%
Haze	ASTM D 1003	2	%

DEFECTS

DEFECT SIZE

MAXIMUM PER SQUARE FOOT

Defect Properties

Pinholes, pits, dimples	.030"-.039"	0
	.020"-.029"	1
	.010"-.019"	5
Scratches/Fibers	.250" > (length)	0
	.250" < (length)	1

FLAMMABILITY

MAXIMUM REQUIREMENTS

RESULTS

Flammability-FAR 25.853(a) Appendix F(a)(F)(i)

Material results for 0.060"

Self Extinguish Time	15 seconds max	0 seconds
Burn Length	6"	0.10"
Average Drippings	3 seconds	0 seconds

Material also passes FAR 25.853(a) Appendix F(a)(1)(ii), 12 second vertical burn test