

Royalite® R59

Fire-rated sheet



Product Description

Royalite® R59 thermoplastic sheet provides a unique PVC/ABS product that meets many industry flammability standards. It is recognized under the component program of Underwriters Laboratories, Inc. with a classification of 94V-1 at 0.058", 94V-0 at 0.085" and 94-5VA at 0.085". It combines very high impact strength with excellent ductility and formability.

Technical Properties

Property	Test Method	Value*
Specific Gravity (color dependent)	ASTM D-792	1.18 - 1.25
Tensile Strength	ASTM D-638	5,000 psi
Flexural Strength	ASTM D-790	7,800 psi
Flexural Modulus	ASTM D-790	280,000 psi
Izod Impact (Notched) 72°F	ASTM D-256	8.0 ft-lbs/in
Izod Impact (Notched) -40°C	ASTM D-256	1.8 ft-lbs/in
Rockwell Hardness (R Scale)	ASTM D-785	93
Heat Deflection Temperature (@264 psi - annealed)	ASTM D-648	175°F
Coefficient of Linear Thermal Expansion	ASTM D-696	4.6 - 5.5x10 ⁻⁵ in/in/°F
Mold Shrinkage	Internal	0.005 - 0.007 in/in
Motor Vehicle Safety Standard	FMVSS 302	Passes
Flammability	UL 94 V-0	Listed @ 0.085"
Flammability	UL 94-5VA	Listed @ 0.085"
Radiant Panel (Flame Spread Index)	UL 94	RP50
Relative Thermal Index (Electrical)	UL 746	85°C at ≥ 0.086"
Relative Thermal Index (Mech. w/impact)	UL 746	70°C ≥ 0.086"
Relative Thermal Index (Mech. w/o impact)	UL 746	85°C ≥ 0.086"
Ball Pressure Test (72°C, 3.00 mm)	IEC 60695-10-2	Passes

**All values based on 0.125" unless otherwise stated*

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Professional Plastics assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale

NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

www.professionalplastics.com

sales@proplas.com

USA (888) 995-7767 – Singapore +65 6266-6193 – 台灣 Taiwan +886 (3) 535 7850