



Silflex Typical Properties

Property	Performance
Physical	
Specific Gravity, g/cu. cm.	2.55 – 2.58
Elongation at Break, percent	4.5 – 4.9
Tensile Strength, psi @ 22°C	500,000 - 550,000
Water Absorbency @ 22°C, 65% R.H.	None
Chemical	
Resistance to Acids and Alkalies	Excellent in weak solutions. Fair in concentrated solutions..
Resistance to Solvents	Fair
Resistance to the Elements	Good Sunlight and weathering properties.
Compatibility	Improved compatibility with most potting compounds and varnishes.
Moisture Vapor Resistance	Excellent
Electrical	
Dielectric Strength	Provides only space factor electrical insulation of approximately 650 volts.
Volume Resistivity @ 22°C and 500 volts dc, ohm-cm	$10^{15} - 10^{16}$
Dielectric Constant @ 22°C, 60 Hz	6.5 – 6.8
Dissipation Factor @ 22°C, 1 MHz	0.001 – 0.005
Thermal	
Thermal Endurance	Up to 200°C indefinitely.
Brittleness Temperature	- 56°C per ASTM D746
Flame Resistance	Passes UL 1441 (VW-1). Will not burn.
Notes:	

Average properties of bulk S Glass as reported in Owens Corning Publication No. 5-TEX-18027, considered to be applicable to bare glass filaments. Information contained here is precise and reliable. However being unique, each end-use should be evaluated to satisfy its specific requirements.

Order Online at:

www.professionalplastics.com/Silflex_Sleeving

Email: sales@proplas.com

USA (888) 995-7767 – Singapore +65 6266-6193 – 台湾 Taiwan +886 (3) 5357850