

# VINCON<sup>®</sup> FLEXIBLE PVC TUBING

## FORMULATION C-219-A

### TECHNICAL DATA

#### TYPICAL PHYSICAL PROPERTIES

Property	ASTM Method	Value or Rating
Durometer Hardness (Shore A), 15s	D2240-02	67
Tensile Strength, psi (MPa)	D412-98	2,450 (16.9)
Ultimate Elongation, %	D412-98	400
Tear Resistance, lb-f/inch (kN/m)	D1004-94	180 (31.5)
Compression Set Constant Deflection, % @158°F (70°C) for 22 hours	D395-01 Method B	65
Brittle Temperature, °F (°C)	D746-98	-45 (-43)
Specific Gravity	D792-00	1.21
Water Absorption, %	D570-98	0.12
Maximum Recommended Operating Temperature, °F (°C)	-	165 (74)
Color	-	Clear

Unless otherwise noted, all tests were conducted at room temperature (73°F). Values shown were determined on 0.075" thick extruded strip or 0.075" thick molded

#### INVENTORIED SIZES

SGPPL Part Number	I.D. (inches)	O.D. (inches)	Wall (inches)	Length (feet)
ABH02002	1/16	1/8	1/32	100
ABH02007	1/8	1/4	1/16	100
ABH02012	3/16	5/16	1/16	100
ABH02013	3/16	3/8	3/32	100
ABH02014	3/16	7/16	1/8	100
ABH02017	1/4	3/8	1/16	100
ABH02018	1/4	7/16	3/32	100
ABH02019	1/4	1/2	1/8	100
ABH02022	5/16	7/16	1/16	100
ABH02023	5/16	1/2	3/32	100
ABH02027	3/8	1/2	1/16	100
ABH02028	3/8	9/16	3/32	100
ABH02029	3/8	5/8	1/8	100
ABH02032	7/16	9/16	1/16	100
ABH02033	7/16	5/8	3/32	100
ABH02036	1/2	5/8	1/16	100
ABH02037	1/2	11/16	3/32	100
ABH02038	1/2	3/4	1/8	100
ABH02039	1/2	13/16	5/32	100
ABH02041	9/16	3/4	3/32	100
ABH02045	5/8	13/16	3/32	100

SGPPL Part Number	I.D. (inches)	O.D. (inches)	Wall (inches)	Length (feet)
ABH02046	5/8	7/8	1/8	100
ABH02053	3/4	1	1/8	100
ABH02054	3/4	1-1/16	5/32	100
ABH02055	3/4	1-1/8	3/16	100
ABH02057	3/4	1-1/4	1/4	100
ABH02059	7/8	1-1/8	1/8	100
ABH00062	1	1-1/4	1/8	50
ABH00064	1	1-3/8	3/16	50
ABH00065	1	1-1/2	1/4	50
ABH00070	1-1/4	1-5/8	3/16	50
ABH00071	1-1/4	1-3/4	1/4	50
ABH00073	1-1/2	1-7/8	3/16	50
ABH00074	1-1/2	2	1/4	50
ABH00076	1-3/4	2-1/4	1/4	50
ABH00078	2	2-1/2	1/4	50
ABH00082	2-1/2	3	1/4	50
ABH00085	3	3-1/2	1/4	50
ABH05077	2	2-3/8	3/16	20
ABH05078	2	2-1/2	1/4	20
ABH05082	2-1/2	3	1/4	20
ABH05085	3	3-1/2	1/4	20



Saint-Gobain Performance Plastics Corporation  
2664 Gilchrist Road, Akron, OH 44305  
330-798-9240 • 800-798-1554 • 330-798-6968  
www.tygon.com



**IMPORTANT:** It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics tubing for all intended uses. Laboratory and clinical tests must be conducted in accordance with applicable regulatory requirements in order to determine the safety and effectiveness for use of tubing in any particular application.

For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product to be free from defects in materials and workmanship. Our only obligation will be to replace any portion proving defective or at our option to refund the purchase price thereof. User assumes all other risk, if any, including the risk of injury, loss or damage, direct or consequential, arising out of the use, misuse, or inability to use this product. THIS WARRANTY IS IN LIEU OF THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED. No deviation is authorized.

Saint-Gobain Performance Plastics Corporation assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to those products. All such advice is given and accepted at the buyer's risk.