

FLAMETEC™ CP-5 FLAME RETARDENT POLYPROPYLENE

TYPICAL PHYSICAL PROPERTIES	Nominal Value	Units	ASTM Test Method
Melt Index	1.5	g/cm ³	D 1238
Density	0.99	g/cm ³	D 1238
Tensile Strength @ Yield	3,500	psi	D 638
Elongation at Yeild	10	%	D 638
Coefficient of Linear Thermal Expansion	6.5x10 ⁻⁵	In./In.°C	D696
Flexural Modulus	135,000	psi	D 790
Notched Izod Impact	17	fl-lb/in	D 256
Low Temperature Brittleness F ₅₀			
Heat Deflection Temperature @ 66 psi	86	°C	D 648
Maximum Service Temperature, Air	180	°C	Long Term
Vicat Softening Point	129	°C	D 1525
Hardness, Shore D	65		D 2240
Absorption	Max.0.01%		D 5709(2)
Flammability Rating	UL94-VO		UL94-VO
Compliances	ETL Labs	VO	per UL 94 Test



801 E. Corey Street, Scranton PA 18505
 Phone: (800) 235-8320
 Fax: (800) 858-9266
www.vycomplastics.com

Physical properties of plastic sheeting are represented as "Typical". Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation, and is not to be construed as a representation or warranty expressed or implied. Our warranties are limited to those expressly stated in formal contracts or in conditions of sale on our invoices and order acceptances. Conditions and methods of use may vary and are beyond the control of Vycom; therefore, Vycom disclaims any liability incurred as a result of the use of this product in accordance with the data contained in our physical property charts. No information herein shall be construed as an offer of indemnity for infringement or as a recommendation to use the products in such a manner as to infringe any patent, domestic or foreign.

The "Typical" properties of our plastic sheet cannot be automatically used when engineering finished components; and the fabricator or end user is responsible for insuring the suitability of our products for their specific application or end use!