

Meldin® 7001 and 7021

Typical Properties for Isostatically Molded Material

Property	Temperature °F (°C)	ASTM Method	Units	Meldin® 7001	Meldin® 7021
Mechanical					
Tensile Strength	75 (24)	D-638	psi (MPa)	12,500 (86)	10,100 (70)
Tensile Elongation	75 (24)	D-638	%	9.3	5.6
Tensile Strength	500 (260)	D-638	psi (MPa)	5,400 (37)	5,500 (38)
Tensile Elongation	500 (260)	D-638	%	4.5	4.3
Flexural Strength	75 (24)	D-790	psi (MPa)	15,200 (105)	15,600 (108)
Flexural Modulus	75 (24)	D-790	psi (MPa)	460,000 (3172)	570,000 (3930)
Compressive Strength	75 (24)	D-695	psi (MPa)	25,200 (174)	25,300 (174)
Compressive Stress @ 1% Strain	75 (24)	D-695	psi (MPa)	1,500 (10)	1,600 (10)
Compressive Stress @ 10% Strain	75 (24)	D-695	psi (MPa)	17,200 (119)	17,100 (118)
Compressive Modulus	75 (24)	D-695	psi (MPa)	290,000 (2000)	326,000 (2248)
Thermal					
Coefficient of Thermal Expansion	75-500 (24-260)	E-831	in/in/°F x 10e-5 (m/m/°C x 10e-5)	2.7 (5)	4.5 (8)
Electric					
Dielectric Strength	75 (24)	D-149	volts/mil (MV/m)	450 (18)	104 (4)
Miscellaneous					
Specific Gravity	75 (24)	D-792	–	1.43	1.51
Hardness	75 (24)	D-785	Rockwell E	64	50
Water Absorption, 24 hours	75 (24)	D-570	%	0.23	0.2



Meldin® 7001



Meldin® 7021

Warranty Information: All information contained herein is believed to be correct but is presented without any guaranty, warranty or representation of any kind, express or implied. Technical data set forth herein is based on tests and measurements conducted in our laboratory under controlled conditions. Suggestions concerning possible applications of our products are made without representation or warranty that such use is free from patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other such measures may not be required.

Saint-Gobain Performance Plastics

386 Metacom Avenue
Bristol, RI 02809
Tel: 401-253-2000
www.rulon-meldin.com

Meldin® is a registered trademark.

©2007 Saint-Gobain Performance Plastics Corporation
BST-4150-1M-0907-SGCS