# SABIC Innovative Plastics™

## Lexan\* 9440 Sheet

# Product Datasheet

#### Description

Lexan 9440 uncoated polycarbonate sheet is formulated to meet the requirements of specialty applications as food handling/contact, medical device/apparatus, and other clean room needs. Lexan 9440 sheet complies with FDA food additive regulations (21 CFR 177.1580) and meets USP-VI criteria. Lexan 9440 sheet offers high impact performance, thermoformability, transparency and dimensional stability.

# Typical Property Values •

Property	Test Method	Unit	Value
Physical			
Specific Gravity	ASTM D792	-	1.20
Water absorption, equilibrium, 24 Hrs.	ASTM D570	%	0.15
@ 73º F			0.35
@ 212º F			0.58
Light Transmission (avg.) 1/8" disk	ASTM D1003	%	88
Mechanical			
Tensile Strength	ASTM D638	psi	
@ Yield			9,000
@Ultimate			9,500
Elongation	ASTMD638	%	110
Tensile Modulus	ASTM D638	psi	345,000
Flexural Modulus	ASTM D790	psi	345,000
Flexural Strength	ASTM D790	psi	13,500
Compressive Strength	ASTM D695	psi	12,500
Compressive Modulus	ASTMD695	psi	345,500
Elongation	ASTM D638	%	110
Izod Impact Strength,	ASTM D256A	ft-lbs/in	
Notched @ 1/8"			12-16
Unnotched @ 1/8"			60 (no failure)
Thermal			
Heat deflection temperature	ASTM D648	٥F	
@ 264 psi			270
@ 66 psi			280
Coeff.of Thermal Expansion	ASTM D696	in/in/ºF	3.75 x 10 <sup>-5</sup>
Thermal Conductivity	ASTM C177	Btu/hr x ft <sup>2</sup> x °F x in	1.35

These property values have been derived from Lexan\* resin data for the material used to produce this sheet product. Variation within normal tolerances are possible for various colors. These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC Innovative Plastics representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection molded samples. All samples are prepared according ISO 294.

\* Trademarks of SABIC Innovative Plastics IP BV

### Lexan\*



### Lexan\* 9440 Sheet

#### Product Availability

Product code:	Lexan 9440 – polycling masking
	Lexan 9444 – cling stick white masking
Standard size:	48 x 96 inches
Textures:	Polished/Polished
Colors:	Clear 112

Other colors/sizes are available by special request.



\* Trademark of SABIC Innovative Plastics IP BV

Americas: SABIC Innovative Plastics Specialty Film & Sheet One Plastics Avenue Pittsfield, MA 01201 USA Tel. (1) (413) 448 5400 Fax. (1) (413) 448 7506 Toll free: 1-800 451 3147 Europe: SABIC Innovative Plastics Specialty Film & Sheet Plasticslaan 1 NL - 4612 PX Bergen op Zoom The Netherlands Tel. (31) (164) 292911 Fax. (31) (164) 293272 Pacific: SABIC Innovative Plastics Specialty Film & Sheet 1266 Nanjin Road (W) Plaza 66, 17th Floor 200040 Shanghai, China Tel. (86) 21 62881088 Fax. (86) 21 62880818

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT http://www.sabic-ip.com AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller's or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

\* Trademark of SABIC Innovative Plastics IP BV

www.sabic-ip.com