

## RT500X TECHNICAL DATA BULLETIN

GRADE: RT500X NEMA LI 1-1998 GRADE: G-10 U.L. LISTED: N

DESCRIPTION: The RT500X has excellent electrical properties under humid conditions and very good heat resistance and mechanical properties. RT500X is used when NEMA recognition is needed and fine machining is required. This version is made with an extra-fine weave fabric. RT500X also complies with ANSI/NEMA IM 60000-2021 Grade G-10, MIL-I-24768/2, Type GEE and ASTM D709 Type IV Grade G-10.

## **TYPICAL PROPERTIES**

			VALUE
		UNITS	Specimen Tested (ID x OD)
			0.75" x 1.00"
PHYSICAL PROPERTIES			
Specific Gravity			
(ASTM D792)		-	1.90
Rockwell Hardness			
(ASTM D785)		M Scale	110
Moisture Absorption	Condition D <sub>1</sub> -24/23		
(ASTM D570)		%	0.07
Tensile Strength	Condition A		
(ASTM D638)		psi	50,000
Compressive Strength	Condition A		
(ASTM D695)		psi	44,000
Compressive Modulus	Condition A		
(ASTM D695)		kpsi	1,065



## **RT500X - TYPICAL PROPERTIES (continued)**

		UNITS	VALUE Specimen Tested (ID x OD)	
			0.75" x 1.00"	
THERMAL PROPERT	TIES			
Temperature Index <sup>1</sup>	Electrical / Mechanical	°C	200 / 200	
Tg by DMA	Condition A	°C	≥ 170	
Flammability Rating (UL Bulletin 94)	Condition A	Class	НВ	
ELECTRICAL PROPI	ERTIES			
Dissipation Factor @ 1 MHz (ASTM D150)	Condition A	-	0.024	
	Condition D-24/23	-	0.034	
Relative Permittivity @ 1 MHz (ASTM D150)	Condition A	-	4.39	
	Condition D-24/23	-	4.46	
Breakdown Voltage (ASTM D149)	Condition A	kVolts	65	
	Condition D-48/50	kVolts	75	
Electric Strength (ASTM D149)	Condition A	Volts/mil	495	
	Condition D-48/50	Volts/mil	500	

<sup>&</sup>lt;sup>1</sup> NEMA LI-6: This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to contact Customer Service, or preferably our web site, www.norplex-micarta.com, to determine if information is the most current.

Specification writers: Contact Norplex-Micarta for specification values before submission.